

Sisalation® Foam Cell Multipurpose LT


Description

Sisalation® Foam Cell Multipurpose LT is a 3-in-1 multipurpose sarking solution. It is an Extra Heavy Duty sarking material consisting of a foam core laminated between layers of reflective foil, with an anti-glare coating for installation safety.

Application

Sisalation® Foam Cell Multipurpose LT is specifically designed for use in wall and roof applications. It is designed for use in both commercial and residential applications, subject to the product limitations outlined below.

Product composition



Features and benefits

Easy installation	→	Produced in rolls that are easy to move and install.
150mm wide flap	→	Can be installed without the need for tape, saving time and cost.
R0.2 Thermal Resistance	→	Acts as a thermal break for steel frames.
Australian made	→	Supporting local manufacture.

Product data

Nominal thickness mm	Width mm	Overlap/flap mm	Length m	Area per roll m ²	Nominal weight per roll kg	Product code
8.4	1350	150	22.25	30	18	4006747

Physical properties

Property		Test method/standard	Result	Unit
Thermal Resistance R-value		AS/NZS 4859.1	R0.2	m ² K/W
Duty Classification		AS 4200.1 Table 1	Extra Heavy Duty	
Water Control		AS/NZS 4201.4	Water Barrier	
Vapour Control		AS 4200.1	Class 2 Vapour Barrier	
Vapour Permeance		ASTM E96	< 0.1429	µg/Ns
Emittance	Reflective side	AS/NZS 4201.5	IR Reflective (0.03)	
	Anti-glare side		IR Semi-Reflective (0.14)	
Resistance to dry delamination		AS/NZS 4201.1	Pass	
Resistance to wet delamination		AS/NZS 4201.2	Pass	
Shrinkage		AS/NZS 4201.3	≤ 0.5	%
Electrical Conductivity		AS/NZS 3100	Electrically Conductive	

Fire hazard properties

Sisalation® Foam Cell Multipurpose LT exhibits the following characteristics when tested in accordance with the following:

Property	Test method/Standard	Result
Flammability Index	AS/NZS 1530.2	≤ 5 (Low)
Early Fire Hazard Indices	AS/NZS 1530.3	
Ignitability Index		0
Spread of Flame Index		0
Heat Evolved Index		0
Smoke Developed Index		1
BAL Compliance	AS 3959	Roof: Low-40 Wall: Low-FZ

Product limitations

- **Important: Do Not Modify This Product:** Compliance with the evidence of suitability data referenced in this document is only achieved by the product or configuration listed.
- This product is not classified as non-combustible in accordance with AS1530.1 and is not suitable where a non-combustible material is required.
- As this product exceeds 1mm in thickness it is not suitable for use where a non-combustible material is required, in accordance with NCC2022 Volume 1 C2D10(6)(f), and NCC2025 Volume 1 C2D10(6)(f), NCC 2022 Volume 2 H3D2(1)(f), NCC 2025 Volume 2 H3D2(1)(f).
- This product does not have a Group Number in accordance with AS 5637.1 (NCC 2022 Volume 1 S7C4, NCC 2025 Volume 1 S7C4) and is not suitable as an exposed internal wall and ceiling lining where a group number is required
- This product is not vapour permeable and must not be used where the cladding manufacturer specifies a vapour permeable membrane.
- This product is a Class 2 Vapour Barrier and is not suitable where a pliable building membrane or sarking-type material is required in:
 - Climate Zones 4-8 per NCC 2022 Volume 1 F8D3 and ABCB Housing Provisions Standard 2022 10.8.1
 - No cavity applications in Climate Zone 3 and all construction in Climate Zone 4-8 per NCC Volume 1 F8D3 & ABCB Housing Provisions 2025 10.8.1
- This product is not suitable as a substitute for safety mesh or a fall-arrest system.
- Sisalation® Foam Cell products are not designed to withstand prolonged weathering - exterior cladding should be installed within 6 weeks in a wall application, or 2 weeks in a roof application. Products exposed for longer than these periods will not be covered by the Product Warranty.

- This product is not suitable for use within 500m of a saltwater body in unenclosed or permanently ventilated spaces.
- Compression of the product will reduce its declared material R-value.
- Additional mechanical fasteners may be required for product exposed to adverse weather conditions.
- Product must be inspected for damage and repaired/replaced prior to cladding being installed.

Compliance

NCC 2022

Sisalation® Foam Cell Multipurpose LT, when specified and installed correctly, meets the following compliances:

- Meets the requirements of NCC 2022 Volume 1 F3D3 as a sarking-type material complying with AS 4200.1
- Meets the requirements of NCC 2022 Volume 1 F8D3(1)(a) & Housing Provisions 10.8.1(1)(a) through compliance with AS 4200.1.
- Complies to NCC Volume 1 2022 J4D3(1) and ABCB Housing provisions 2022 13.2.2(1) meeting requirements through compliance with AS/NZS 4859.1.
- When tested to AS/NZS 1530.2 this product does not exceed the 'Flammability index' as required by NCC 2022 Volume 1, S7C7 for Sarking-Type materials: In other locations.
- When tested to AS/NZS 1530.3 this product does not exceed the 'Spread of Flame' and 'Smoke Developed' as required by NCC 2022 Volume 1, S7C7 for insulation materials.

NCC 2025

Sisalation® Foam Cell Multipurpose LT, when specified and installed correctly, meets the following compliances:

- Meets the requirements of NCC 2025 Volume 1 F1D13 as a sarking-type material complying with AS 4200.1.
- Meets the requirements of NCC 2025 Volume 1 F8D3(1)(a) & Housing Provisions 10.8.1(1)(a) through compliance with AS 4200.1.
- Complies to NCC Volume 1 2025 J4D3(1) and ABCB Housing Provisions 2025 13.2.2(1) meeting requirements through compliance with AS/NZS 4859.1.
- When tested to AS/NZS 1530.2 this product does not exceed the 'Flammability index' as required by NCC 2025 Volume 1, S7C7 for Sarking-Type materials: In other locations.
- When tested to AS/NZS 1530.3 this product does not exceed the 'Spread of Flame' and 'Smoke Developed' as required by NCC 2025 Volume 1, S7C7 for insulation materials.

Thermal performance

The thermal performance of Sisalation® Foam Cell Multipurpose LT varies with application, orientation and installation method. Please find thermal system properties in the below table.

Thermal system properties

The following table provides indicative Total R-value calculations based on typical systems. To determine the Total R-value for a broader range of system types, contact the Fletcher Insulation Technical team at technical@insulation.com.au

	Pitched metal roof	Double brick cavity wall
Heat Flow In (Summer)	R2.1	R1.7
Heat Flow Out (Winter)	R1.3	R1.7

Pitched metal roof based on 22.5° pitch with 40mm unventilated air gap, Sisalation® Foam Cell Multipurpose LT, unventilated roof space and 10mm flat plasterboard ceiling.

Double brick cavity wall based on 110mm clay brick, 20mm unventilated air space both sides and Sisalation® Foam Cell Multipurpose LT.

Maintenance and conditions of use

- Use of pressure cleaners or mineral based cleaners must not be used on the foil facing product.
- Where Sisalation® Foam Cell products can be inspected, ensure any tears are repaired with appropriate tape, such as Vapastop® 883 Foil Tape.
- When storing, ensure product is protected from all physical damage at all times. Avoid storing product packaging under UV light (direct sunlight) for extended periods.

- Sisalation® Foam Cell products must be kept dry at all times, out of contact with direct sunlight and out of contact with alkaline products, cement and mortar as well as corrosive environments such as chlorine.
- Products exposed to harsh weather conditions prior to cladding must be inspected for damage and repaired or replaced to ensure compliance with the Product Warranty.
- Sisalation® Foam Cell shall be installed in accordance with AS/NZS 4200.2 'Pliable Building Membranes and Underlays – Installation Requirements for Metal Roofs, Tile Roofs and Walls Membranes and Underlays – Installation Requirements for Metal Roofs, Tile Roofs and Walls'
- Building Designer to consider the suitability of this product based on the projects design requirements.

Health and safety

Sisalation® Foam Cell Multipurpose LT contains aluminium foil and can conduct electricity. To avoid electrocution, care should be taken to ensure products do not come into contact with electrical wiring during installation or use. Sisalation® Foam Cell Multipurpose LT contains no substances which at their given concentration, are hazardous to health. Refer to SUI5 for more information.

Environmental properties

No ozone depleting substances are used in the manufacture or composition of Sisalation® Foam Cell Multipurpose LT. Specification of Sisalation® Foam Cell Multipurpose LT provides the use of ODP free insulation while also ensuring that no harmful levels of Volatile Organic Compounds (VOCs) are released. This allows for the incorporation of environmentally preferable insulation whilst also maintaining indoor air quality.

Technical specification

When specifying, please state the following: The insulation shall be Sisalation® Foam Cell Multipurpose LT with a Material R-value of R0.2 and an Extra Heavy Duty rating in accordance with AS/NZS 4200.1. Supplied by Fletcher Insulation, the insulation material shall be installed in accordance with Fletcher Insulation installation guidelines available for download via www.insulation.com.au

© Fletcher Insulation Pty Limited 2026. Fletcher Insulation reserves the right to change product specifications without prior notification. Information in this publication and otherwise supplied to users as to the subject product is based on our general experience and is given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or is to be implied with respect to either such information or the product itself, in particular the suitability of the product for any particular purpose. The purchaser should independently determine the suitability of the product for the intended application. The colour PINK, Pink® and Pink Batts® are registered trademarks of Owens Corning Intellectual Capital, LLC used under licence by Fletcher Insulation. FBS-1 Glasswool Bio-Soluble Insulation® is a registered trademark of ICANZ. Unless otherwise stated, all ™ and ® are trademarks and registered trademarks of Fletcher Insulation Pty Limited ABN 72 001 175 355. FTDS22_Revision_9_Issue Date 03092026.